

## **Supplementary Information**

### **Doped h-BN monolayer as efficient noble metal-free catalysts for CO oxidation: role of dopant and water in activity and catalytic de-poisoning**

S. Sinthika, E. Mathan Kumar and Ranjit Thapa\*

SRM Research Institute, SRM University, Kattankulathur-603203, Tamil Nadu, India

\*Corresponding Author Email: ranjit.t@res.srmuniv.ac.in

#### **Contain:**

**Fig. S1**

**Fig. S2**


**Fig. S3**

**Details of microkinetic modelling and Sabatier Activity for LH mechanism**


**Details of microkinetic modelling and Sabatier Analysis for ER mechanism**

**Fig. S4**

**Fig. S5**



**Fig. S1** Partial density of states of a CO molecule adsorbing on CBN surface pre-adsorbed with O<sub>2</sub>. Strong hybridization between O<sub>2</sub> valence states and the CBN surface indicate strong bonding to the surface. The O<sub>2</sub> molecule acquires electrons while the donor levels of CBN become empty. From the PDOS of the CO molecule, we find that the states of CO are almost unaffected, implying that CO does not interact with the surface.




**Fig. S2** Schematic of the reaction pathway of the ER mechanism in OBN surface. (a) The initial state is taken to be the case when the reactants and the surface are non interacting (b) The adsorption of O<sub>2</sub>, which is exothermic (c) the reaction of the first CO with the adsorbed oxygen, resulting in an atomic O adsorbed to the surface (d) the reaction of the second CO with the atomic oxygen to form two CO<sub>2</sub> molecules, that easily desorb from the surface.

The charge density difference has been calculated with respect to the fragments as

$$\Delta\rho = \rho_{\text{O}_2 \dots \text{CO}@\text{OBN}} - (\rho_{\text{O}_2 \dots \text{CO}} + \rho_{\text{OBN}})$$

where  $\rho_{\text{O}_2 \dots \text{CO}@\text{OBN}}$  is the electron density of the total  $\text{O}_2 \dots \text{CO} + \text{OBN}$  system, and  $\rho_{\text{O}_2 \dots \text{CO}}$  and  $\rho_{\text{OBN}}$  are the unperturbed electron densities of the sorbate and substrate, respectively.

Electron accumulation on the B-C bond indicates strong chemisorptions of the intermediate with the surface.



**Fig. S3** Charge density difference plots of the intermediate  $\text{O}_2 \dots \text{CO}$  on the OBN surface, shown along planes perpendicular to (a) CO (b)  $\text{O}_2$ . Red and blue regions indicate the electron accumulation and loss.

### Microkinetic Modelling for Sabatier Activity:

The Sabatier activity was calculated using the microkinetic model for the LH mechanism as follows:

The reaction proceeds as:



R1 and R2 denote the adsorption of CO and O<sub>2</sub> respectively while in R3, the simultaneous adsorption of the two reactants results in a stable intermediate that reacts to form CO<sub>2</sub>.

Reactions R1 and R2 are assumed to be in equilibrium so that the forward and reverse rates are equal:

$$k_1^+ p(\text{CO}) \theta_* = k_1^- \theta_{\text{CO}}$$

$$\theta_{\text{CO}} = K_1 p(\text{CO}) \theta_* \quad \text{and}$$

$$k_2^+ p(\text{O}_2) \theta_* = k_2^- \theta_{\text{O}_2}$$

$$\theta_{\text{O}_2} = K_2 p(\text{O}_2) \theta_*$$

The rate determining step is R3 and hence the rate of CO<sub>2</sub> formation can be taken as the maximum of the rate of the reaction R3. Sabatier activity is the upper bound of the reaction rate R3, considering its forward rate alone:

$$(\text{R3})_{\text{max}} = k_3^+ \theta_{\text{CO}} \theta_{\text{O}_2} = k_3^+ K_1 p(\text{CO}) \theta_* K_2 p(\text{O}_2) \theta_*$$

Here,

$$k_3^+ = \frac{kT}{h} e^{\frac{-E_a}{kT}}$$

E<sub>a</sub> is the activation energy for CO<sub>2</sub> formation.

K<sub>i</sub> is the equilibrium constant of reaction i,

p(CO) and p(O<sub>2</sub>) are the partial pressures of CO and O<sub>2</sub>: p(CO) = 0.01 bar and p(O<sub>2</sub>) = 0.21 bar at room temperature,

k<sub>i</sub><sup>+</sup> and k<sub>i</sub><sup>-</sup> are the forward and backward rate constants for Ri respectively.

In order to calculate the coverages of CO and O<sub>2</sub> in terms of the free sites (θ<sub>\*</sub>) we employ the rule,

$$\theta_{\text{O}_2} + \theta_{\text{CO}} + \theta_* = 1$$
$$\theta_* = \frac{1}{1 + K_1 p(\text{CO}) + K_2 p(\text{O}_2)}$$

With the rate constants given by

$$K_1 = e^{\frac{-\Delta G_1}{kT}}$$

where  $\Delta G_1 = \Delta E_1 - T\Delta S_1$  is the change in Gibb's free energy of R1

$\Delta E_1$  is the adsorption energy of CO

$\Delta S_1$  is the change in entropy during CO adsorption

$k$  is the Boltzmann constant

$T$  is the temperature.

$$K_2 = e^{\frac{-\Delta G_2}{kT}}$$

where  $\Delta G_2 = \Delta E_2 - T\Delta S_2$  is the change in Gibb's free energy of R2

$\Delta E_2$  is the adsorption energy of O<sub>2</sub>



$\Delta S_2$  is the change in entropy during O<sub>2</sub> adsorption

Finally, the Sabatier activity is calculated as

$$Activity = kT \ln\left(\frac{(R3)_{max}}{h/kT}\right)$$

### **Microkinetic Modelling and Sabatier Analysis for ER mechanism:**

The reaction proceeds as follows:



Assuming that reaction R1 is in equilibrium, we get

$$\theta_{O_2} = K_1 p(O_2) \theta_*$$

The formation of CO<sub>2</sub> (R2) is rate determining. The maximum of the rate R2 is calculated as the forward rate,

$$(R2)_{max} = k_2^+ p(CO) \theta_{O_2}$$

Where

$$k_2^+ = \frac{kT}{h} e^{\frac{-E_a}{kT}}$$

Since the sum of coverages of the reactants and free sites has to be 1, we get

$$\theta_* + \theta_{O_2} = 1$$

$$\theta_* = \frac{1}{1 + K_1 p(O_2)}$$

Where  $K_1$  is the equilibrium constant for R1 given by,

$$K_1 = e^{\frac{-\Delta G_1}{kT}}$$


where  $\Delta G_1 = \Delta E_1 - T\Delta S_1$  is the change in Gibb's free energy of R1

$\Delta E_1$  is the adsorption energy of O<sub>2</sub>

$\Delta S_1$  is the change in entropy during O<sub>2</sub> adsorption


The Sabatier Activity is defined as

$$Activity = kT \ln\left(\frac{(R2)_{max}}{h/kT}\right)$$



**Fig. S4:** Local configurations of the reactants on the Au<sub>55</sub> and Pt<sub>55</sub> clusters along the minimum-energy pathway for the formation of first CO<sub>2</sub>. The reaction energies with reference to free (O<sub>2</sub> and two CO) molecule and surface (taken as 0 eV) are given beneath each Fig..





**Fig. S5:** Free energy pathways for CO oxidation via ER mechanism on C doped h-BN with graphitic substrate.